

X6Cr17 https://www.steelss.com High Quality Special Steel Supplier +86-13880247006 E-mail:sales@steelss.com

X6Cr17

Cold heading and cold extruding steels; technical delivery conditions for stainless steels X6Cr17 steel chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of X6Cr17, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Materials Stainless Steels Cold heading and cold extruding steels; technical delivery conditions for stainless steels X6Cr17

| X6Cr17 Standard Number | | | | | |
|------------------------|-----------------------|--|--|--|--|
| ITEM | Standard Number | Descriptions | | | |
| 1 | DIN 1654-5 (1989) | Cold heading and cold extruding steels; technical delivery conditions for stainless steels | | | |
| 2 | DIN 17440 (1996) | Stainless steels - Technical delivery conditions for drawn wire | | | |
| 3 | DIN 17455 (1985) | Welded circular tubes of stainless steels for general requirements; technical delivery conditions | | | |
| 4 | DIN 17456 (1985) | Seamless circular tubes of stainless steels for general requirements; technical delivery conditions | | | |
| 5 | DIN EN 10088-3 | Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes | | | |
| 6 | DIN EN 10088-4 | Stainless steels - Part 4: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for construction purposes | | | |
| 7 | DIN EN 10088-5 | Stainless steels - Part 5: Technical delivery conditions for bars, rods, wire, sections and bright products of corrosion resisting steels for construction purposes | | | |
| 8 | DIN EN 10297-2 (2005) | Seamless circular steel tubes for mechanical and general engineering purposes - Technical delivery conditions - Part 2: Stainless steel | | | |
| 9 | DIN EN 10088-1 | Stainless steels - Part 1: List of stainless steels | | | |
| 10 | DIN EN 10088-2 | Stainless steels - Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes | | | |



X6Cr17 https://www.steelss.com High Quality Special Steel Supplier +86-13880247006 E-mail:sales@steelss.com

| 11 | DIN 17456 (1985) | Seamless circular tubes of stainless steels for general requirements; technical delivery conditions |
|----|-----------------------|--|
| 12 | DIN 5512-3 | Materials for rail vehicles - Steels - Part 3: Stainless steel flat products; Selected standard |
| 13 | DIN EN 10151 | Stainless steel strip for springs - Technical delivery conditions |
| 14 | DIN EN 10250-4 | Open die steel forgings for general engineering purposes - Part 4: Stainless steels |
| 15 | DIN EN 10263-5 | Steel rod, bars and steel wire for cold heading and cold extrusion - Part 5: Technical delivery conditions for stainless steels |
| 16 | DIN EN 10296-2 (2005) | Welded circular steel tubes for mechanical and general engineering purposes - Technical delivery conditions - Part 2: Stainless steel |

| X6Cr17 Chemical composition(mass fraction)(wt.%) | | | | | | | | | |
|--|----|----|----|---------|----|----|---------|----|-------|
| Chemical | | | | Min.(%) | | | Max.(%) | | |
| С | | | | | | | 0.08 | | |
| | Si | | | | | | 1.00 | | |
| Mn | | | | | | | 1.00 | | |
| Р | | | | | | | 0.040 | | |
| S | | | | | | | 0.015 | | |
| Cr | | | | 16.0 | | | 18.0 | | |
| С | Si | Mn | Р | S | Cr | Ni | Мо | V | Та |
| | | | | | | | | | |
| W | Ν | Cu | Co | Pb | В | Nb | AI | Ti | Other |
| | | | | | | | | | |

| X6Cr17 Physical Properties | | | | | | |
|----------------------------|---------|----------|--|--|--|--|
| Tensile strength | 115-234 | b/MPa | | | | |
| Yield Strength | 23 | 0.2 /MPa | | | | |
| Elongation | 65 | 5 (%) | | | | |
| | - | (%) | | | | |
| Akv | - | Akv /J | | | | |
| HBS | 123-321 | - | | | | |



X6Cr17 https://www.steelss.com High Quality Special Steel Supplier **Ionghai** High Quality Special Steel Supplier +86-13880247006 E-mail:sales@steelss.com

HRC 30 _ X6Cr17 Mechanical Properties b/MPa 231-231 Tensile strength 0.2 /MPa Yield Strength 154 56 5 (%) Elongation (%) Akv /J Akv 235-268 HBS 30 HRC

| X6Cr17 Heat Treatment Regime | | | | | | |
|------------------------------|-----------|-----------|-------------|-------|--|--|
| Annealing | Quenching | Tempering | Normalizing | Q & T | | |
| ? | ? | ? | ? | ? | | |

| X6Cr17 Range of products | | | | | | |
|--------------------------|---|-------------------------------|---|--|--|--|
| Product type | Products | Dimension | Processes | Deliver Status | | |
| Plates / Sheets | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling and cold rolling | Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting | | |
| Steel Bar | Round Bar, Flat Bar, Square Bar | 8-1200mm*L | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting, | | |
| Coil / Strip | Steel Coil /Steel Strip | 0.03-16.0x1200mm | Cold-Rolled & Hot- Rolled | Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting | | |
| Pipes / Tubes | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded | Annealed, Solution and Aging, Q+T, ACID- WASHED | | |

We can produce Stainless Steels the specifications follows:

Note:

(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.



Mechanical properties Mechanische Eigenschaften

(3) from the standard for 50 mm (2 in).

X6Cr17 https://www.steelss.com High Quality Special Steel Supplier +86-13880247006 E-mail:sales@steelss.com

(2) in the ASTM A6 standard specified scope can meet any additional conditions.

Caracteristiques mecaniques ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale Rm Tensile strength / Zugfestigkeit / Resistance a la traction A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc Round bar: Diameter: 1mm-2000mm Square bar: Size: 50mm * 50mm-600mm *600mm Plate steel/flat bar: Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm Tube/pipe: Size: OD: 6-219mm WT: 1-35 mm. Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm Length: We can supply any length based on the customer's requirement. Forging/hot rolling/ extrusion of steel. Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode. Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement. UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402 Excellent service for all kinds of industries, with advantages of technologies, equipment and price. We serve you with our honesty, integrity, and professionality.